

Zirconia material selection guide

Durable materials, right design

		MgPSZ		Y-TZP		ATZ
		Izory®	Izory®HD	Dark HIPed	HIPed	HIPed

PROPERTY	TEST METHOD	Izory®	Izory®HD	Dark HIPed	HIPed	HIPed
Color		Ivory	Ivory	Tan	White or Gray	White
Chemistry (%)	ICP & EDS					
ZrO ₂ + HfO ₂ + MgO		99.50	97.14			
Y ₂ O ₃ + HfO ₂ + ZrO ₂				99.50	99.70	89.95
Al ₂ O ₃				0.25	0.25	10.00
Other	0.5	0.50	2.86	0.25	0.05	0.05
Density [g/cm ³]	ISO 18754	5.75	5.78	6.08	6.08	5.79
Water absorption	ASTM-373	nil	nil	nil	nil	nil
Grain Size [μm]	ASTM E-112	70	20	0.4	0.4	0.7
Fracture Toughness K _{IC} [MPa·m ^{1/2}]	ASTM C-1421 - Chevron Notch	10	10	5	5	9
Loop Abrasion [mm ³]	ASTM G-174	0.150	0.100	0.100	0.100	0.020
Modulus of Elasticity MOE [GPa]	ASTM E-1876-99	214	214	214	214	296
Modulus of Rupture 4 pt MOR [MPa]	ASTM C-1161	575	650	1350	1350	1050
Hardness Vickers [HV 1]	ASTM C-1327-08	1050	1225	1425	1660	1430
Poisson Ratio	ASTM E-1876-99	0.31	0.31	0.32	0.32	0.27
Compressive Strength [MPa]	ASTM C-773	1760	1760	2580	2580	2100
Thermal Conductivity RT [W/m·°K]	ASTM C-408	2.50	2.50	2.18	2.18	6.00
Coefficient of Thermal Exp. X10 ⁻⁶ /°C (25-1000°C)	ASTM C-372	10.2	10.2	10.7	10.7	9.0
Maximum Material Use Limit [°C]	No Load	500	500	1500	1500	1500



NOTES: Typical values are not intended to be used as a specification. Contact Refractron for application suitability.

Contact:
 1.315.573.1134
 adamo@refractron.com
 www.refractron.com
 Newark, NY 14513, USA

follow us:

